

# Last Deck

## VLP-8148.10

### CCT-I Test Results

Panel #	Sample Desc.	DFT.	Substrate
712	PLX-2823-02	3.3	Aluminum
713	PLX-2823-02	2.7	Aluminum
714	PLX-2823-02	2.9	Aluminum
715	PLX-2823-02	2.7	Aluminum
716	PLX-2823-02	3	Aluminum
717	PLX-2823-02	4	Aluminum

500 hrs		2-Jan
SC	FR	BL
<1	10	None
<1	10	None
<1	10	None
<1	10	None
<1	10	None
<1	10	None

1000 hrs		23-Jan
SC	FR	BL
<1	9	none
<1	10	none
<1	10	none
<1	10	none
<1	10	none
<1	10	none