

Florida Exposure Testing

Panel #	Substrate	Sample Desc.	DFT.	Original		Color Scale	ill/obs	6 Month			12 Month		
				60°	20°			60°	20°	DE*	60°	20°	DE*
2681	ACT B-1000	PLX-2287-01	3.0	5.5	1.1	FMC2	D65/10	5.4	1	1.70	N/A	N/A	N/A
2682	ACT B-1000	PLX-2287-01	3.3	5.2	1	FMC2	D65/10	N/A	N/A	N/A			
2683	ACT B-1000	PLX-2822-04	4	5.6	1.1	FMC2	D65/10	5.5	1	2.56	N/A	N/A	N/A
2684	ACT B-1000	PLX-2822-04	4	5.4	1.1	FMC2	D65/10	N/A	N/A	N/A			

6mo: 2681 PLX2287-01, no visual change gloss, slight lightening.
 2683 PLX2822-04, no visual change in gloss, some lightening.